





Solid state electrolyte dramatically reduces thermal runaway caused by abuse.

☑ Super Fast Charging (0.5C)

M High Power Density

Nominal Capacity	40Ah (0.5C)
Nominal Voltage	3.6V
Charging Voltage	4.2V
Voltage Termination	2.5V
Charging Specifications	
Super Fast Charging	2C (120A), 95%
Fast Charging	2C (62A) constant current (CC) charges to 4.2v, then constant voltage (CV) charging until the charging current is less than 0.02C (0.6A)
Standard Charging	1C (40A) constant current (CC) charges to 4.2v, then constant voltage (CV) charging until the charging current is less than 0.02C (0.6A)
Discharging Specifications	
Pulse Discharging	3C (durations < 10S)
Continous High Rate Discharging (Max)	2C
Standard Discharging	1C
Cycle Life	1C/1C 2400 times 100% DOD with 80%SoH
	1C/2C 1600 times 100% DOD with 80%SoH
	2C/2C 1000 times 100% DOD with 80%SoH
Operating Temperatures	
Charging Temperature	-10°C to 0°C / 14°F to 32°F (0.1C Charging)
	0°C to 60°C / 32°F to 140°F (1C Charging)
	10°C to 45°C / 50°F to 113°F (2C Charging)
Discharging Temperature	-30°C to 60°C / -22°F to 140°F
Internal Resistance	1.1+/-0.5mΩ
Weight	400g +/-15g / ~0.88 lb
Energy Density	> 360Wh/kg (0.5C/0.5C)
Volume Density	> 700Wh/L
Dimensions	10.8 x 87 x 187mm / 0.43 x 3.43 x 7.36 in

Select More Power Cells by Key Characteristics:

• AX-01 Power Cell

Solid state electrolyte.

- Fast Charging (2C)
- High Energy Density
- AX-02 Power Cell

Solid state electrolyte.

- Super Fast Charging (4C)
- High Power Density

• AX-02.5 Power Cell

Solid state electrolyte within a smaller body.

- Super Fast Charging (4C)
- High Power Density

• LiFePo Power Cell

Lithium Ion power cell within a smaller body.

- Super Fast Charging (4C)

ACCESS PRODUCT PAGE

GO TO WEBSITE







